



MIRELON® AKUSTIK

PEF - EN 14313 - ST(+) 90 – ST(-) -40 - WS 005 - CL 5 - PH 6,5

Thermoacoustic insulation from polyethylene foam with closed cell structure

MIRELON® AKUSTIK is a hose designed for thermoacoustic insulation of water drain.

MIRELON® AKUSTIK is an ideal thermal insulation material for new buildings, adaptations and renovations due to its excellent thermal insulation properties, flexibility and easy workability.

MISAPPLICATION:

- Thermal insulation of low and high pressure steam distribution systems
- Outdoor instalation without surface protection against weathering and UV radiation
- Instalation in places where the ambient temperature exceeds 90°C

Technical data:

- non-laminated design
- wall thickness: 5 mm (according to EN 14313:2009+A1:2013)
- diameter: from 75 to 160 cm (according to EN 14313:2009+A1:2013)
- length: 15 m (according to EN 14313:2009+A1:2013)

Color: blue

MIRELON® AKUSTIK– physical properties

Basic characteristic		Properties				Harmonized technical specification
Thermal resistance	Coefficient of thermal conductivity W/m.K	°C	λ _D	°C	λ _D	EN 14313:2009+A1:2013
		-20	0,039	20	0,049	
		0	0,044	50	0,057	
		10	0,046	90	0,069	
	Dimensions and tolerations					
	- wall thickness	5 mm	+/- 1 mm	X	X	
	- diameter	75 mm	+ 2 to 6 mm	110-160 mm	+ 3 to 8 mm	
	- lenght	L +/- 1,5%				
Reaction on fire	Reaction on fire	F-s3, d2				
Thermal resistance stability in aging/degradation	Coefficient of thermal conductivity W/m.K	see table above				
	Dimensions and tolerations	see table above				
	Dimension stability	3%				
	Characteristic stability	it does not change				
	Lowest operating temperature	-40°C				
	Highest operating temperature	90°C				
Thermal resistance stability at high temperature	Characteristic stability	it does not change				
	Dimension stability	3%				
	Highest operating temperature	90°C				

NPD – no property has been determined



Basic characteristic		Properties	Harmonized technical specification
Stability of reaction on fire at high temperature	Characteristic stability	it does not change	EN 14313:2009+A1:2013
Stability of reaction on fire in aging/degradation	Characteristic stability	it does not change	
Compressive strength	-	NPD	
Water permeability	Water absorption	WS 005 ($W_p \leq 0,05$)	
Water vapor permeability	Water absorption	NPD	
	Diffusion resistance	NPD	
Release of corrosive substances	Trace amount of soluble ions and pH	CL 5 (≤ 5 mg/kg), PH 6,5	
Sound absorption index	Structure sound transmission	NPD	
	Sound absorption	NPD	
Release of hazardous substances into internal environment	Release of hazardous substances	NPD	
Burning by incandescent glow	Burning by incandescent glow	NPD	

NPD – no property has been determined

The technical datasheet was drawn up on the basis of the protocols of the notified bodies: no. 1023 (Institut pro testování a certifikaci a.s., třída Tomáše Bati 299, Louky, 763 02 Zlín) a no. 1390 (Centrum stavebního inženýrství a.s., ul. Pražská 16, 102 00 Praha 10).

Approved 18. 12. 2024

CE			
1023, 1390			
Mirel Vratimov a.s., Mourová 114/7, 739 32 Vratimov tel. 596 732 673, e-mail: mirel@mirelon.com			
12			
POV 15/2024/EN			
EN 14313+A1			
MIRELON® AKUSTIK			
Thermal insulation products for use as thermal insulation for equipment, buildings and industrial installation			
ThIBELI			
Coefficient of thermal conductivity W/m.K			
°C	λ _D	°C	λ _D
-20	0,039	20	0,049
0	0,044	50	0,057
10	0,046	90	0,069
reaction on fire		F-s3, d2	
wall thickness		5 mm	
PEF - EN 14313 - ST(+)-90-ST(-)-40 - WS 005 - CL 5 - PH 6,5			

