



MIRELON® sealing cord

12 PEF - EN 14313 - ST(+) 90 – ST(-) -40 - WS 005 - CL 5 - PH 6,5

Thermoinsulating sealing cord from polyethylene foam with closed cell structure

MIRELON® sealing cord is a flexible cord from full polyethylen foam profile for sealing dynamically stressed joints and cracks.

MIRELON® sealing cord is an ideal material for use in expansion joints of cast floors and in window and door frame installation thanks to its properties. Furthermore, it can be used to seal the fillings in the frames between the panel joints and all joints created in the building industry.

MISAPPLICATION:

- Thermal insulation of low and high pressure steam distribution systems
- Outdoor installation without surface protection against weathering and UV radiation
- Installation in places where the ambient temperature exceeds 90°C

Technical data:

- non-laminated design
- length: 1,2 to 500 m according to cord diameter (according to EN 14313:2009+A1:2013) (the total length can be divided into several strands)
- diameter: 6 to 70 mm (according to EN 14313:2009+A1:2013)

Color: gray-black

MIRELON® sealing cord – physical properties

Basic characteristics		Properties				Harmonized technical specification
Thermal resistance	Coefficient of thermal conductivity W/m.K	°C	λ_D	°C	λ_D	EN 14313:2009+A1:2013
		-20	0,039	20	0,049	
		0	0,044	50	0,057	
		10	0,046	90	0,069	
	Dimensions and tolerations					
- diameter	6 mm (including)	+/- 1 mm	15 to 30 mm (including)	+/- 2,5 mm		
	6 to 10 mm (including)	+/- 1,5 mm	above 30 mm	+/- 4 mm		
	10 to 15 mm (including)	+/- 2 mm	X	X		
- sealing cord length	L -1,5% + 2,5%					
Reaction on fire	Reaction on fire	E _l -s3, d2				
Thermal resistance stability in aging/degradation	Coefficient of thermal conductivity W/m.K	see table above				
	Dimensions and tolerations	see table above				
	Dimension stability	3%				
	Characteristic stability	it does not change				
	Lowest operating temperature	-40°C				
Highest operating temperature	90°C					
Thermal resistance stability at high temperature	Characteristic stability	it does not change				
	Dimension stability	3%				
	Highest operating temperature	90°C				

NPD – no property has been determined




Basic characteristics		Properties	Harmonized technical specification
Stability of reaction on fire at high temperature	Characteristic stability	it does not change	EN 14313:2009+A1:2013
Stability of reaction on fire in aging/degradation	Characteristic stability	it does not change	
Compressive strength	-	NPD	
Water permeability	Water absorption	WS 005 ($W_p \leq 0,05$)	
Water vapor permeability	Water absorption	NPD	
	Diffusion resistance	NPD	
Release of corrosive substances	Trace amount of soluble ions and pH	CL 5 (≤ 5 mg/kg), PH 6,5	
Sound absorption index	Structure sound transmission	NPD	
	Sound absorption	NPD	
Release of hazardous substances into internal environment	Release of hazardous substances	NPD	
Burning by incandescent glow	Burning by incandescent glow	NPD	

NPD – no property has been determined

The technical datasheet was drawn up on the basis of the protocols of the notified bodies: no. 1023 (Institut pro testování a certifikaci a.s., třída Tomáše Bati 299, Louky, 763 02 Zlín) a no. 1390 (Centrum stavebního inženýrství a.s., ul. Pražská 16, 102 00 Praha 10).

Approved 20.3.2020

			
1023, 1390			
Mirel Vratimov a.s.			
Mourová 114/7, 739 32 Vratimov			
12			
POV 10/2020/EN			
EN 14313+A1			
MIRELON[®] sealing cord			
Thermal insulation products for use as thermal insulation for equipment, buildings and industrial installation			
ThIBEII			
Coefficient of thermal conductivity W/m.K			
°C	λ_0	°C	λ_0
-20	0,039	20	0,049
0	0,044	50	0,057
10	0,046	90	0,069
reaction on fire	E ₁ -s3, d2		
diameter	see table below		
PEF - EN 14313 - ST(+) 90 - ST(-) -40 - WS 005 - CL 5 - PH 6,5			
sealing cord diameter			
6, 8, 10, 12, 15, 20, 25, 30, 40, 50, 60 a 70 mm			