

rel The difference is in quality ...



Mirel Vratimov a.s., Mourová 114/7, 73932 Vratimov, tel.: +420 596 732 673, fax: +420 596 732 693, IČO: 25912020, DIČ: CZ25912020



Thermoinsulating strip from polyethylene foam with closed cell structure

MIRELON® PANEL laminated by PET/PETZ is panel designed to insulate walls, ceilings, floors, roofs, water reservoirs, tanks, large-diameter heating and air distribution systems. Suitable for insulation in areas where washability is necessary for hygienic reasons (food plants).

MIRELON® PANEL laminated by PET/PETZ is an ideal thermal insulation material for new buildings, adaptations and renovations due to its excellent thermal insulation properties, flexibility and easy workability.

MISAPPLICATION:

- Thermal insulation of low and high pressure steam distribution systems
- Outdoor instalation without surface protection against weathering and UV radiation
- Instalation in places where the ambient temperature exceeds 90°C
- Use of a self-adhesive strip to fastening of a strip with thickness 20 mm or more to vertical surfaces and ceilings

Technical data:

- laminated design, can be provided with self-adhesive layer
- panel thickness: 15, 20, 25, 30, 40, 50, 60, 70 and 80 mm (according to EN 14313:2009+A1:2013)
- panel width: 100 cm (according to EN 14313:2009+A1:2013)
- panel lenght: 2 m (according to EN 14313:2009+A1:2013)

Color: gray-black, white

MIRELON® PANEL laminated by PET/PETZ – physical properties

Basic characteristic		Properties				Harmonized technical specification
Thermal resistance		$^{\circ}$ C	λ _D	$^{\circ}\!\mathbb{C}$	$\lambda_{\scriptscriptstyle D}$	
	Coefficient of thermal	-20	0,039	20	0,049	
	conductivity W/m.K	0	0,044	50	0,057	
		10	0,046	90	0,069	
	Dimesions and tolerations					
	- panel thickness	15 mm	+/- 2 mm	> 30 mm	+/- 3,5 mm	
		20 - 30 mm	+/- 2,5 mm	Х	Х	
	- panel width	Š +/- 1%	•			
	- panel lenght	L +/- 1,5%				
Reaction on fire	Reaction on fire		F-s	EN 14313:2009+A1:2013		
Thermal resistance stability in aging/degradation	Coefficient of thermal		see tal			
	conductivity W/m.K					
	Dimesions and tolerations	see table above				
	Dimension stability	3%				
	Characteristic stability	it does not change				
	Lowest operating temperature	-40°C				
	Highest operating temperature	90℃				
at high temperature	Characteristic stability	it does not change				
	Dimension stability	3%				
	Highest operating temperature		9	0°C		

NPD - no property has been determined





relThe difference is in quality ...




Mirel Vratimov a.s., Mourová 114/7, 73932 Vratimov, tel.: +420 596 732 673, fax: +420 596 732 693, IČO: 25912020, DIČ: CZ25912020

Basic characteristic		Properties	Harmonized technical specification	
Stability of reaction on fire at high temperature	Characteristic stability	it does not change		
Stability of reaction on fire in aging/degradation	Characteristic stability	it does not change		
Compressive strengh	trengh - NPD			
Water permeability	ty Water absorption WS 005 (W _p ≤ 0,05)			
Water vapor permeability	Water absorption	NPD		
	Diffusion resistance	NPD		
Release of corrosive substances	Trace amount of soluble ions and pH	CL 5 (≤ 5 mg/kg), PH 6,5	EN 14313:2009+A1:2013	
Sound absorption index	Structure sound transmission	NPD		
	Sound absorption	NPD		
Release of hazardous substances into internal environment	Release of hazardous			
Burning by incadescent glow	Burning by incadescent glow NPD			

NPD – no property has been determined

The technical datasheet was drawn up on the basis of the protocols of the notified bodies: no. 1023 (Institut pro testování a certifikaci a.s., třída Tomáše Bati 299, Louky, 763 02 Zlín) and no. 1390 (Centrum stavebního inženýrství a.s., ul. Pražská 16, 102 00 Praha 10).

Approved 26. 5. 2022



panel thickness 15, 20, 25, 30, 40, 50, 60, 70 a 80 mm

