



MIRELON® STRIP laminated by AL/ALZ

PEF - EN 14313 - ST(+)-90 - ST(-)-40 - WS 005 - CL 5 - PH 6,5

Thermoinsulating strip from polyethylene foam with closed cell structure

MIRELON® STRIP laminated by AL/ALZ is strip designed to insulate walls, ceilings, floors, roofs, water reservoirs, tanks, large-diameter heating and air distribution systems. Suitable for insulation in areas where washability is necessary for hygienic reasons (food plants).

MIRELON® STRIP laminated by AL/ALZ is an ideal thermal insulation material for new buildings, adaptations and renovations due to its excellent thermal insulation properties, flexibility and easy workability.

MISAPPLICATION:

- Thermal insulation of low and high pressure steam distribution systems
- Instalation in places where the ambient temperature exceeds 90°C
- Use of a self-adhesive strip to fastening of a strip with thickness 20 mm or more to vertical surfaces and ceilings

Technical data:

- laminated design, can be provided with self-adhesive layer
- strip thickness: 2, 3, 4, 5, 6, 8, 10, 15, 20, 25, 30, 40 a 50 mm (according to EN 14313:2009+A1:2013)
- strip width: 100 cm (according to EN 14313:2009+A1:2013)
- strip length: 2 až 400 m according to strip thickness (according to EN 14313:2009+A1:2013)

Color: gray-black, white

MIRELON® STRIP laminated by AL/ALZ – physical properties

Basic characteristics		Properties				Harmonized technical specification	
Thermal resistance	Coefficient of thermal conductivity W/m.K	°C	λ_D	°C	λ_D	EN 14313:2009+A1:2013	
		-20	0,039	20	0,049		
		0	0,044	50	0,057		
		10	0,046	90	0,069		
	Dimensions and tolerations						
	- strip thickness	2 - 5 mm	+/- 1 mm	20 and 30 mm	+/- 2,5 mm		
	6 - 10 mm	+/- 1,5 mm	> 30 mm	+/- 3,5 mm			
	15 mm	+/- 2 mm	X	X			
- strip width	Š +/- 1%						
- strip length	L +/- 1,5%						
Reaction on fire	Reaction on fire	F-s3, d2					
Thermal resistance stability in aging/degradation	Coefficient of thermal conductivity W/m.K	see table above					
	Dimensions and tolerations	see table above					
	Dimension stability	3%					
	Characteristic stability	it does not change					
	Lowest operating temperature	-40°C					
Highest operating temperature	90°C						


NPD – no property has been determined

Basic characteristics		Properties	Harmonized technical specification
Thermal resistance stability at high temperature	Characteristic stability	it does not change	EN 14313:2009+A1:2013
	Dimension stability	3%	
	Highest operating temperature	90°C	
Stability of reaction on fire at high temperature	Characteristic stability	it does not change	
Stability of reaction on fire in aging/degradation	Characteristic stability	it does not change	
Compressive strength	-	NPD	
Water permeability	Water absorption	WS 005 ($W_B \leq 0,05$)	
	Diffusion resistance	NPD	
Water vapor permeability	Water absorption	NPD	
	Diffusion resistance	NPD	
Release of corrosive substances	Trace amount of soluble ions and pH	CL 5 (≤ 5 mg/kg), PH 6,5	
Sound absorption index	Structure sound transmission	NPD	
	Sound absorption	NPD	
Release of hazardous substances into the internal environment	Release of hazardous substances	NPD	
Burning by incandescent glow	Burning by incandescent glow	NPD	

NPD – no property has been determined

The technical datasheet was drawn up on the basis of the protocols of the notified bodies: no. 1023 (Institut pro testování a certifikaci a.s., třída Tomáše Bati 299, Louky, 763 02 Zlín) a no. 1390 (Centrum stavebního inženýrství a.s., ul. Pražská 16, 102 00 Praha 10).

Approved 25.5.2022

			
1023, 1390			
Mirel Vratimov a.s. Mourová 114/7, 739 32 Vratimov 12 POV 7/2022/EN EN 14313+A1			
MIRELON® STRIP laminated by AL/ALZ Thermal insulation products for use as thermal insulation for equipment, buildings and industrial installation ThB/EII			
Coefficient of thermal conductivity W/m.K			
°C	λ_D	°C	λ_D
-20	0,039	20	0,049
0	0,044	50	0,057
10	0,046	90	0,069
reaction on fire		F-s3, d2	
strip thickness		see table below	
PEF - EN 14313 - ST(+) 90 - ST(-) -40 - WS 005 - CL 5 - PH 6,5			

strip thickness
2, 3, 4, 5, 6, 8, 10, 15, 20, 25, 30, 40 a 50 mm

